



## **Bitumen Emulsion Specification**

### **K2**

Property	Result
Particle charge	Pos.
Residue on 710 um KS sieve (%)(m/m), maximum	0.05
Residue on 150 um KS sieve (g per 100 mL), maximum	0.15
Binder content (%)(m/m), minimum	57
Viscosity (degrees Engler (°E) at 20°C)	10 max.
Viscosity redwood No. II (s at 85°C)	-
Storage stability (long period test) % water content difference, maximum	2