



Bitumen Emulsion Specification

K1-70

Property	Result
Particle charge	Pos.
Residue on 710 um KS sieve (m/m), maximum	-
Residue on 150 um KS sieve (g per 100 mL), maximum	-
Binder content (m/m), minimum	67
Viscosity (degrees Engler (°E) at 20°C)	-
Viscosity redwood No. II (s at 85°C)	25-35
Storage stability (long period test) % water content difference, maximum	-